

TECHNICAL DATA SHEET

T103

T103 is a **Polypropylene Homopolymer**, produced by the **Spheripol Technology**.

T103 combines exceptional processability with excellent Stiffness, Clarity & Gloss

T103 is recommended for Thermoforming of Cups, Containers & other miscellaneous disposable items

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 ⁰ C)	ASTM D1238	g/10 min	4
Density at 23°C	ASTM D1505	g/cm ³	0.90
Tensile Strength at Yield	ASTM D638	MPa	37
Tensile Elongation at Yield		%	8
Flexural Modulus	ASTM D790	MPa	1700
Izod Impact Strength (Notch, 23°C)	ASTM D256	J/m	60
Vicat Softening Point (10N)	ASTM D1525	°C	154
Heat Deflection Temperature (0.46 N/m ²)	ASTM D648	°C	95

Suggested Processing Temperature

Barrel Temperature	°C	190 – 230
Die Temperature	°C	220 – 250

* Halene P is the registered trademark of Polypropylene of HPL
 Mechanical properties tested on Injection Molded Test Specimens

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.
 Visit us at www.haldiapetrochemicals.com

HPL/PP/Rev009/2019